

NAME	VISABLE LIGHT TRANSMISSION	REFLECTION	U VALUE	SHADING COEFFICIENT
6MM CLEAR FLOAT	87%	7%	5.8	0.94
6MM FRENCH GREEN	71%	7%	6.1	0.65
6MM GREY	45%	6%	6.1	0.65
6MM GREY ECLIPSE ADVANTAGE	32%	9%	3.8	0.48
6MM CLEAR ECLIPSE ADVANTAGE	66%	22%	3.8	0.71
6MM BRONZE ECLIPSE ADVANTAGE	40%	11%	3.8	0.53
6MM EVER GREEN ECLIPSE ADV	49%	14%	3.8	0.43
6MM BLUE-GREEN ECLIPSE ADV	56%	17%	3.8	0.53
6.38 COMFORT PLUS CLEAR	80%	10%	3.6	0.77
6.38 COMFORT PLUS GREY	39%	6%	3.6	0.57
6.38 COMFORT PLUS GREEN	70%	10%	3.6	0.57
6.38 COMFORT PLUS NEUTREL	58%	7%	3.6	0.6
6MM FRENCH GREEN SOLARFLEX	25%	31%	6.1	0.41
6.38 GREY	42%	5%	5.7	0.71
6.00 EVERGREEN	66%	8%	5.8	0.6